

Product Information

KEMPEROL® 2K-PUR

Work pack includes:

Component A: Cream Formulation, Component B: Dark Brown Formulation

Product Description

KEMPEROL® 2K-PUR is a two-component, UV-stable, “odor-free,” solvent free, Low VOC, high performance cold liquid-applied waterproofing and roofing resin.

KEMPEROL® 2K-PUR reinforced membrane system can be surfaced with traffic coatings, reflective coatings, aggregate surfacing coatings and other granular materials to achieve a desired function and appearance.

Composition & Materials

A monolithic membrane is created in the field by combining the KEMPEROL® 2K-PUR two-part, cold liquid-applied reactive-cure polyurethane resin with KEMPEROL® polyester reinforcing fleece. Membrane may be applied using standard fleece available in 4, 8, 10, 13, 20, 27, and 41-inch nominal widths.

Use

KEMPEROL® 2K-PUR membrane is suitable for a wide range of interior and exterior applications including roofs, plazas, planters, foundations, mechanical rooms and other waterproofing applications.

Limitations

Interior or exterior applications of KEMPEROL® 2K-PUR membrane exposed to UV-light may yellow or discolor. Use of a coating or aggregate surfacing systems are recommended where color-fast applications are required.

KEMPEROL® 2K-PUR may be applied when the ambient temperature is 41 °F (5 °C) and rising, and the substrate temperature is a minimum of 5 degrees above the dew point. The maximum application temperature is approximately 90 °F (32 °C).

Note: Viscosity increases with falling temperature. For temperatures below 50 °F (10 °C), KEMPEROL® A 2K-PUR Accelerator should be added to component A to reduce set time.

Yield

Using 165 Fleece: 38 ft² (3.53 m²) per 12.5 kg work pack.
Using 120 Fleece: 45 ft² (4.20 m²) per 12.5 kg workpack.

Note: All yields are approximate and may vary depending upon smoothness and absorbency of substrate.

Storage

Always store in cool and dry location. Do not store in direct sunlight or in temperatures below 35 °F (1.7 °C) or above 80 °F (27 °C). Approximate shelf life 12 months with proper storage.

For best use, 24 hours before application, the material is to be acclimated at temperatures between 65-70 °F (18-21 °C).

Precautions

Review Safety Data Sheets before handling, available online at kempersystem.net.

Surface Preparation

All surfaces must be free from gross irregularities, loose, unsound or foreign material such as dirt, ice, snow, water, grease, oil, release agents, lacquers, or any other condition that would be detrimental to adhesion of the primer and membrane. This requires careful preparation of existing horizontal and vertical substrates; cracks are filled, expansion joints are prepared, flashings are removed or modified, and termination points are determined. Substrates and penetrations are prepared to rigorous industry standards, and may require scarifying, sandblasting or grinding in some cases to achieve a suitable substrate.

Priming

After substrate preparation, temporary watertightness may be achieved with the application of KEMPERTEC® D Primer or EP Primer and temporary joint filler. Alternatively, the use of quick-dry KEMPERTEC® R or EP5 Primer may allow same-day membrane application. Refer to the appropriate KEMPERTEC® primer data sheet for application instructions.

Headquarters: **Kemper System America, Inc.** | 1200 North America Drive | West Seneca, NY 14224
Customer/Technical Service: Phone (800) 541-5455 | Fax (201) 767-4304 | inquiry@kempersystem.net

Sustainability Information	
Rapidly Renewable Resource	80%
Recycled Content % (post / pre)	0 / 0
Manufacture Location	Buffalo, NY, USA

Allow primer to cure completely prior to application of the KEMPEROL® membrane.

Note: Prior to opening the containers of KEMPEROL® 2K-PUR Resin, wear appropriate safety glasses and protect hands and wrists by wearing gauntlet-type neoprene gloves.

Mixing of Resin

Step 1: Mix resin Component A (cream formulation) with a spiral agitator until the liquid is a uniform cream color.

Step 2: If the ambient temperature is below 50°F (10°C), A2K-PUR Accelerator, a cold weather additive, should be mixed into the Component A. The accelerator should be mixed with the spiral agitator for 2 minutes or until both liquids are thoroughly blended.

Step 3: Add hardener Component B (dark brown formulation) to Component A and mix with a spiral agitator for 2 minutes or until both liquids are thoroughly blended.

NOTE: DO NOT break down workpacks into smaller quantities – mix the entire workpack.

Application (165 Fleece)

Step 1: After the Resin is mixed, using a Kemperol roller nap or brush apply 2/3 of the resin liberally and evenly onto the surface in even stroke. Covering one working area at a time, between 10 - 15 ft².

Step 2: Roll the Kemperol Fleece directly into the Resin, making sure the SMOOTH SIDE IS FACING UP (natural unrolling procedure), avoiding folds and wrinkles. Use the roller or brush to work the resin into the fleece, saturating from the bottom up. The appearance of the fleece should be light opaque yellow/gray with no white spots. White spots are indications of unsaturated fleece or lack of adhesion. It is important to correct these areas before proceeding.

Step 2: Roll the Kemperol Fleece directly into the Resin, making sure the SMOOTH SIDE IS FACING UP (natural unrolling procedure), avoiding folds and wrinkles. Use the roller or brush to work the resin into the fleece, saturating from the bottom up. White spots are indications of unsaturated fleece or lack of adhesion. It is important to correct these areas before proceeding.

Surfacing

KEMPEROL® 2K-PUR Membrane accepts a wide variety of KEMPERDUR® topcoats and aggregate surfacings for aesthetic or mechanical wear. The KEMPEROL® 2K-PUR membrane must be surfaced within 16-48 hours of membrane application to ensure proper bond between the membrane and surfacing. After the 48 hour window the membrane will require surface abrasion.

Disposal

Cured 2K-PUR resin may be disposed of in standard landfills. This is accomplished by thoroughly mixing all components. Note: Uncured 2K-PUR resin is considered a hazardous material and must be handled as such, in accordance with local, state and federal regulations. Do not throw uncured resin away.

Ordering Information

KEMPEROL® 2K-PUR Work pack:	Size:
Item#: 327-47-025	0.51 US GAL (1.93L) • 2.5 kg
327-47-055	1.03 US GAL (3.90L) • 5.0 kg
327-47-105	2.41 US GAL (9.12L) • 12.5 kg

Membrane Properties		
Physical Property	Test Method	Value
Color		Yellow-Gray
Physical State		Cures to Solid
Thickness (165 Fleece)		80 mils
VOC Content		6 g/l
Peak Load @ 73 °F, avg.	D5147	>70 lbf/in
Elongation	D5147	Min 30%
Tearing Strength	D5147	90 lbf
Puncture resistance	D5602	56 lbs.
Dimensional stability	D1204	0.15%
Water absorption	D570	>1%
Impact Resistance	D2240	Shore A:75
Water vapor transmission	E96	0.08 Perms
Crack spanning		2 mm/0.08 inch
Short-term temperature resistance		250 °C/482 °F
Usage time*		30 minutes
Water resistant after*		2 hours
Solid to walk on after*		24 hours
Can be driven on after*		48 hours
Apply coating/surfacing after*		16-48 hours
Apply overburden after*		48 hours
Completely hardened*		3 days

** values obtained at 73°F, 50% relative humidity, may vary depending upon air flow, humidity and temperature.*

DISCLAIMER: NO WARRANTY, EXPRESS OR IMPLIED, IS MADE IN THIS DOCUMENT. THE PRODUCT IS NOT CLAIMED TO BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE. User and certified Kemper System America, Inc. (KSA) applicators determine suitability only. See individual KSA product data sheets, MSDS sheets, guide specifications and details for complete information regarding the suitability, application and handling of KSA products.